

Preliminary data sheet.

## LUVOCOM 3F PA<sup>HT</sup> 9826 BK

**Polyamide based material  
black color**

Physical Properties		Test Method	Specimen	Units	Typical Value	
Specific Gravity		ISO 1183	MPTS ISO 3167 A	g/cm <sup>3</sup>	1,20	
Water Absorption	23 °C / 24 h		MPTS ISO 3167 A	%	<0,3	
Melt Flow Rates	MFR	ISO 1133	pellet	g/10 Min		
Melt Volume Rate	MVR	ISO 1133	pellet	cm <sup>3</sup> /10 Min		
Linear Mould Shrinkage	VSR 3mm	DIN 16901	MPTS ISO 3167 A	%	0,3-0,5	
Flamability Behaviour		UL 94	1/16"	-		
Mechanical Properties						
at 23°C/50% rh						
Tensile Strength	σ <sub>zM</sub>	ISO 527	MPTS ISO 3167 A	MPa	67	
Elongation	ε <sub>zM</sub>	ISO 527	MPTS ISO 3167 A	%	4,3	
Modulus of Elasticity	E <sub>t</sub>	ISO 527	MPTS ISO 3167 A	GPa	3	
Flexural Strength	σ <sub>bM</sub>	ISO 178	MPTS ISO 3167 A	MPa		
Flexural Elongation	ε <sub>bM</sub>	ISO 178	MPTS ISO 3167 A	%		
Flexural Modulus	E <sub>3B</sub>	ISO 178	MPTS ISO 3167 A	GPa		
Charpy Impact Strength		ISO 179 1eU	MPTS ISO 3167 A	kJ/m <sup>2</sup>	74	
Charpy Impact Strength	-30°C	ISO 179 1eU	MPTS ISO 3167 A	kJ/m <sup>2</sup>		
Charpy Impact Strength notched		ISO 179 eA	MPTS ISO 3167 A	kJ/m <sup>2</sup>		
Charpy Impact Strength notched	-30°C	ISO 179 eA	MPTS ISO 3167 A	kJ/m <sup>2</sup>		
Thermal Properties						
Vicat Softening Temp.	VST A	DIN ISO 306	MPTS ISO 3167 A	°C		
Heat Distortion Temp.	HDT A	ISO 75	MPTS ISO 3167 A	°C	90	
Continuous Service Temp.		UL 746B	MPTS ISO 3167 A	°C	120	
Maximum (short term) Use Temp.				°C	160	
Coefficient of Thermal Expansion		DIN 53752		10 <sup>-5</sup> /K	0,5	
Thermal Conductivity		HOT-DISK	60x60x3 mm	W/mK	0,3	
Electrical Properties						
Insulation Resistance	Strip electrode	R <sub>25</sub>	DIN/IEC 60167	MPTS ISO 3167 A	Ω	>10 <sup>12</sup>
Surface Resistance		R <sub>OB</sub>	DIN IEC 60093	Ronde 60x4 mm	Ω	>10 <sup>12</sup>
Tribological Properties						
Coeff. of Friction μ	dynamic	15Hz 21N	DIN 51834	MPTS ISO 3167	N/N	
Coeff. of Friction μ		40mm/s 21N	LuV	MPTS ISO 3167	N/N	

### Application Examples

9826

strong and tough parts.

Low influence from moisture and temperature to measures and electrical properties, compared with PA66

Automotive industry, textile- and office machinery, apparatus- and precision engineering.

Preliminary data sheet.

# LUVOCOM 3F PA<sup>HT</sup> 9826 BK

**Polyamide based material  
black color**

## Recommended Processing Instructions

### General

In general LUVOCOM® 3F can be processed on conventional extrusion machines while observing the usual technical guidelines.  
Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder, screw and die should be protected against wear as is usual in the processing of reinforced thermoplastic materials.  
Lengthy dwell times for the melts in the cylinder should be avoided.  
Lower the temperatures during interruptions!

### Predrying

(optional)

It is advisable to predry the granulate with a suitable dryer immediately before processing.  
The granulate may absorb moisture from the air.

Dryer type	Temperature°C	Drying time in h
Dehumidifying dryer	130	6 to 8
Vacuum Dryer	120	4 to 6

### Processing Temperatures

Zone 1	°C	260 to 300
Zone 2	°C	260 to 300
Zone 3	°C	260 to 300
Nozzle	°C	250 to 290
Mass-Temperature	°C	optimum 280

### Delivery Form & Storage

Unless indicated otherwise, the material is delivered as 3mm-long pellets in sealed bags on pallets.  
Preferably storage should be effected in dry and normally temperatured rooms.

### Additional Information

The filament can be wound into standard size spools.

3D Printing parameters may vary from machine to machine, the following settings can be used as an indication:

Nozzle temperature: 270 - 290 °C    Print Bed Temperature: > 50 °C    Layer Thickness: >0,1mm

The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application.

#### Europe and Headquarters

LehmannVossCo. KG  
Alsterufer 19  
20354 Hamburg  
Germany  
Tel +49 40 44 197-250  
Fax +49 40 44 197-487  
Email: luvocom@lehvoss.de

#### North-America

LEHVOSS North America, LLC  
185 South Broad Street  
Pawcatuck, CT 06379  
USA  
Tel +1-855-681-3226  
Fax +1 860 495 2047  
Email: info@lehvoss.us

#### Asia

LEHVOSS (Shanghai) Chemical Trading Co., Ltd.  
Unit 4805 Maxdo Centre  
8 Xingyi Road Changning District,  
Shanghai 200336  
China  
Tel +86 21 62785181  
Email: info@lehvoss.cn

